













Rotary seals

Technical datas

Profile	Reference	Material	Pressure	Speed	Temperatures
	RR01	PU + POM	0.5 bars - 0.05 Mpa	5 m/s	-30 to +100°C
		NBR + POM	0.5 bars - 0.05 Mpa	10 m/s	-30 to +100°C
		FKM + PTFE	0.5 bars - 0.05 Mpa	15 m/s	-20 to +220°C
		PTFE	1 bars - 0.1 Mpa	9 m/s	-200 to +200°C
	RR02	PU + POM	0.5 bars - 0.05 Mpa	5 m/s	-30 to +100°C
		NBR + POM	0.5 bars - 0.05 Mpa	10 m/s	-30 to +100°C
		FKM + PTFE	0.5 bars - 0.05 Mpa	15 m/s	-20 to +220°C
		PTFE	1 bars - 0.1 Mpa	9 m/s	-200 to +200°C
	RR05	PTFE	1 bars - 0.1 Mpa	9 m/s	-20 à +220°C
	RR09	PU + POM	400 bars - 40 Mpa	0.2 m/s	-30 to +100°C
		NBR + POM	200 bars - 20 Mpa	0.2 m/s	-30 to +100°C
		FKM + PTFE	200 bars - 20 Mpa	0.2 m/s	-20 to +220°C
		MVQ + PTFE	200 bars - 20 Mpa	0.2 m/s	-50 to +220°C
	RR11	PU	400 bars - 40 Mpa	0.2 m/s	-30 to +100°C
		NBR	160 bars - 16 Mpa	0.2 m/s	-30 to +100°C
		FKM	160 bars - 16 Mpa	0.2 m/s	-20 to +220°C
		PTFE	250 bars - 25 Mpa	0.5 m/s	-200 to +200°C
	RR12	PU	400 bars - 40 Mpa	0.2 m/s	-30 to +100°C
		NBR	160 bars - 16 Mpa	0.2 m/s	-30 to +100°C
		FKM	160 bars - 16 Mpa	0.2 m/s	-20 to +220°C
		PTFE	250 bars - 25 Mpa	0.5 m/s	-200 to +200°C
	RR16	NBR	0 bars - 0 Mpa	15 m/s	-30 to +100°C
		FKM	0 bars - 0 Mpa	15 m/s	-20 to +220°C
		HNBR	0 bars - 0 Mpa	15 m/s	-40 to +150°C
	RR17	NBR	1 bars - 0.1 Mpa		-30 to +100°C
		FKM	1 bars - 0.1 Mpa		-20 to +220°C
		HNBR	1 bars - 0.1 Mpa		-40 to +150°C
	RR18	NBR	0 bars - 0 Mpa	15 m/s	-30 to +100°C
		FKM	0 bars - 0 Mpa	15 m/s	-20 to +220°C
		HNBR	0 bars - 0 Mpa	15 m/s	-40 to +150°C
	RR23	PTFE + NBR	300 bars - 30 Mpa	0.5 m/s	-30 to +100°C
		PTFE + FKM	300 bars - 30 Mpa	0.5 m/s	-20 to +220°C

Designs only for information. Any kind of application, contact us.

3S - Specialized Sealing Solutions

Espace entreprises ALDATU







Rue Léon Larregain

64240 Hasparren - FRANCE



Rotary seals

Technical datas

Profile	Reference	Material	Pressure	Speed	Temperatures
	RR24	PTFE + NBR PTFE + FKM	300 bars - 30 Mpa 300 bars - 30 Mpa	0.5 m/s 0.5 m/s	-30 to +100°C -20 to +220°C
	RR25	PTFE + NBR PTFE + FKM	300 bars - 30 Mpa 300 bars - 30 Mpa	0.5 m/s 0.5 m/s	-30 to +100°C -20 to +220°C
	RR26	PTFE + NBR PTFE + FKM	300 bars - 30 Mpa 300 bars - 30 Mpa	0.5 m/s 0.5 m/s	-30 to +100°C -20 to +220°C
	RR28	PTFE	12 bars - 1.2 Mpa	25 m/s	-30 to +100°C
	RR29	PTFE	150 bars - 15 Mpa	0.5 m/s	-200 to +200°C
	RR30	PTFE	150 bars - 15 Mpa	0.5 m/s	-200 to +200°C

The properties are given as information only. For any application, contact us.

3S - Specialized Sealing Solutions
 Espace entreprises ALDATU
 Rue Léon Larregain
 64240 Hasparren - FRANCE